

Suggested draft requirements for some of the Moldtech texture grades

PATTERN	AVERAGE DEPTH PT IN MICRONS	MINIMUM SUGGESTED DRAFT ANGLE
MT 1055_1	8,89	1,5°
MT-1055_2	16,00	1,5°
MT-1055_3	18,28	1,5°
MT-1055_4	23,62	2°
MT-1055_5	24,64	2°
MT-1055	36,83	3,5°
MT-1055_6	45,46	4°
MT-1055_7	70,86	5,5°
MT-1055_8	78,74	6,5°
MT-11001	4,13	1°
MT-11002	8,26	1,5°
MT-11003	7,67	1,5°
MT-11004	10,51	1,5°
MT-11005	18,77	2°
MT-11006	25,00	2°
MT-11007	55,43	4°

PATTERN	AVERAGE DEPTH PT IN MICRONS	MINIMUM SUGGESTED DRAFT ANGLE
MT 11000	10	1,5°
MT 11010	25	2°
MT 11020	40	3,5°
MT 11030	50	4°
MT 11040	75	6,5°
MT 11050	110	9°
MT 11060	75	6,5°
MT 11070	75	6,5°
MT 11080	50	4°
MT 11090	90	7,5°
MT 11100	150	12,5°
MT 11110	60	5,5°
MT 11120	50	4°
MT 11130	60	5,5°
MT 11140	60	5,5°
MT 11150	70	5,5°
MT 11155	50	8,5°